

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 755 332 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
08.10.1997 Bulletin 1997/41

(21) Application number: **95914303.3**

(22) Date of filing: **24.03.1995**

(51) Int. Cl.⁶: **B41M 5/00**

(86) International application number:
PCT/EP95/01105

(87) International publication number:
WO 95/28284 (26.10.1995 Gazette 1995/46)

(54) RECORDING MATERIAL

AUFZEICHNUNGSMATERIAL

MATERIAU D'ENREGISTREMENT

(84) Designated Contracting States:
AT BE CH DE FR GB IT LI NL

(30) Priority: **14.04.1994 DE 4412817**
27.07.1994 DE 4426578

(43) Date of publication of application:
29.01.1997 Bulletin 1997/05

(73) Proprietor: **Sihl GmbH**
52355 Düren (DE)

(72) Inventors:
• **LIEBLER, Ralf**
D-52372 Kreuzau (DE)
• **KOCH, Peter**
D-50969 Köln (DE)

(74) Representative: **Sternagel, Hans-Günther, Dr. et al**
Patentanwälte Sternagel & Fleischer
Braunsberger Feld 29
51429 Bergisch Gladbach (DE)

(56) References cited:
EP-A- 0 483 798

- **PATENT ABSTRACTS OF JAPAN vol. 18, no. 274 (M-1611) 25 May 1994 & JP,A,06 048 025 (TOPPAN PRINTING COMPANY LIMITED) 22 February 1994**
- **PATENT ABSTRACTS OF JAPAN vol. 4, no. 114 (M-026) 15 August 1980 & JP,A,55 071 586 (FUJI PHOTO FILM COMPANY LIMITED) 29 May 1980**

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 755 332 B1

Description

The invention relates to an improved recording material to meet the requirements of the ink jet process.

Such recording materials are known in principle. They are paper or transparent or dull plastics films. These materials, in particular the plastic films, carry an ink-accepting layer on at least one of their surfaces. These are generally hydrophilic coatings which are applied to the substrate in a thickness of between 2 and 50 μm . Such layers are particularly suitable for accepting the generally aqueous inks.

WO 92/07723 describes the coating of a substrate material with a mixture of a crosslinkable and a liquid-absorbing polymer, a partially-permeable network being formed in the layer after complete reaction of the said polymers.

WO 93/04869 discloses an ink-accepting layer which is composed of the following components: (1) a vinylpyrrolidone, (2) a polyester, (3) an alkylene oxide polymer, (4) a polyvinyl alcohol and (5) a polyether. The layer exhibits particularly good acceptance properties for aqueous inks.

EP-A-524 626 describes a recording material having a layer which consists mainly of porous pseudoboehmite. This coating has the advantage of particularly rapid drying of the ink.

The use of coloured inks in addition to black ink has become established in the production of recordings, in particular image recordings. A wide range of colour effects is achievable by suitable mixing of the primary colours cyan, magenta, yellow and black. In some cases (graphics, advertising, labels), particularly glossy, reflecting colour effects are desirable. Such effects are not achievable by means of conventional known recording materials.

It is the object of the invention to provide a recording material for ink jet processes on which particularly glossy recordings and/or colour effects are achievable with conventional inks.

This object is achieved by an ink-jet recording material having a substrate material which has a metal layer at least on one of its surfaces and has on this metal layer a transparent or slightly dull recording layer for accepting aqueous inks, the gloss measured on the surface of this recording layer according to DIN 67530 having a value > 70% when measured at an angle of 20°, 60° and 85° against the standard gloss master (standard A).

It is usual to measure the gloss at different angles, depending on the gloss. Relatively dull surfaces are usually measured at 85° and more highly glossy surfaces at 20°. The recording material according to the invention has a gloss of more than 70%, preferably of more than 80%, at all conventional measuring angles. A gloss of more than 90% at the measuring angles 60 and 85° and more than 85% at a measuring angle of 20° is very particularly preferred.

The gloss of the recording material is measured on

the recording layer according to DIN 67530 using commercial gloss measuring apparatuses, for example by means of an apparatus obtainable under the name "detectometer" from the company Dr. Lange. The measurement is carried out against the standard gloss master (standard A).

To achieve this gloss of the recording material, the transparent substrate material is provided with a smooth reflecting metal layer on at least one surface by any desired method. Suitable preferred metals are aluminium, zinc, nickel, chromium, copper, gold, silver or the alloys thereof. The application is preferably effected by vapour deposition at reduced pressure or by cathode sputtering over the substrate material arranged in a chamber. The metal layer may also be composed of several individually applied layers in order to obtain the desired thickness. The thickness of the metal layer is preferably 10 nm to 300 nm.

Preferably the metal layer is covered by a protective coating and the transparent or slightly dull recording layer for accepting aqueous inks is positioned on said protective layer.

In order to achieve the desired effect of the metal layer on the surface gloss of the recording layer, the substrate material should have as smooth a surface as possible. This can be achieved by means of a coating on a substrate material, for example paper. A particularly suitable transparent substrate material comprises plastics films of thermoplastic polymers, for example polyester films. Transparent papers are also suitable as substrate material.

In the event of a transparent substrate, said substrate may have a metal layer on one of its surfaces and the transparent or slightly dull recording layer for accepting aqueous inks is positioned on the opposite surface of the transparent substrate material instead of on the metal layer or on the protective coating covering the metal layer.

Suitable polymers for the protective layer are, for example, poly(meth)acrylates, polyvinyl acetates or copolymers thereof.

The transparent recording layer for inks contains a hydrophilic film-forming polymer. Suitable polymers are polyvinyl alcohol (PVA), polyvinylpyrrolidone (PVP), cellulose derivatives, (meth)acrylic acid derivatives, polyvinyl acetate or copolymers thereof and mixtures of such substances. The recording layer may have a thickness of from 2 μm to 50 μm .

This transparent recording layer for inks can, according to the invention, be applied to the following surfaces:

1. to the metal layer
2. to the protective layer covering the metal layer
3. in the case of transparent substrate material, optionally to that surface of the substrate material which faces away from the metal layer.

Since the adhesion of the recording layer to the

metal layer is not completely sufficient in some cases, embodiments 2 and 3 are preferred.

In the case of embodiment 3, the effect of the metal layer also occurs through the transparent substrate material towards the surface of the recording layer.

Examples:

Example 1

A 100 μm thick polyethylene terephthalate film is provided on one side with a 50 nm thick aluminium layer by vapour deposition at reduced pressure. The other surface of the film is then coated with the following solution:

Coating composition:

85 kg of water
15 kg of polyvinylpyrrolidone (PVP)

This coating solution is applied with the aid of a 0.8 mm wire-wound doctor to that surface of the film which faces away from the metal layer and is then dried for 2 minutes at 160°. The resulting coating weight of this ink-accepting layer is about 9 g/m². The recording of an image on this final layer on a commercial ink jet plotter, for example Canon BJC 800, gives particularly interesting reflecting colour effects, in particular colours such as silver, gold, golden red, etc. being produced, which are not achievable by means of a conventional ink jet recording method.

Example 2:

A 100 μm thick polyethylene terephthalate film is provided with an aluminium layer by vapour deposition in the same manner as in Example 1. The coating solution described in Example 1 is then applied to this aluminium layer in the same manner. Here too, recording of an image gives the same interesting colour effects.

Example 3:

A polyethylene terephthalate film is coated by vapour deposition on one side in the same manner as in Example 1. The following protective coating is then applied to this metal layer:

Coating composition:

75 kg of methyl ethyl ketone
10 kg of propylene glycol methyl ether
15 kg of commercial acrylate polymer (solid)

This coating solution is applied to the metal layer by means of a 0.4 mm wire-wound doctor and then dried for about 2 minutes at 160°C. The resulting coating weight of this second layer is about 1.5 g. The ink-

accepting layer is applied to this second layer as described in Example 1. Here too, recording of an image on this final layer on a commercial inkjet plotter gives the same reflecting colour effects.

Claims

1. Ink-jet recording material having a substrate material which has a metal layer at least on one of its surfaces and has on this metal layer a transparent or slightly dull recording layer for accepting aqueous inks, the gloss measured on the surface of this recording layer according to DIN 67530 having a value > 70% when measured at an angle of 20°, 60° and 85° against the standard gloss master (standard A).
2. Recording material according to claim 1, **characterized in that** the metal layer is covered by a protective coating and the transparent or slightly dull recording layer for accepting aqueous inks is positioned on said protective layer.
3. Recording material according to claims 1 or 2, **characterized in that** the substrate material is transparent.
4. Recording material according to claims 1 or 2, **characterized by** a transparent substrate material having a metal layer on one of its surfaces and the transparent or slightly dull recording layer for accepting aqueous inks is positioned on the opposite surface of the transparent substrate material instead on the metal layer or on the protective coating covering the metal layer.
5. Recording material according to claim 1, **characterized in that** the gloss has a value > 80% at an angle of 20°, 60° and 85° against the standard gloss master (standard A).
6. Recording material according to claim 1, **characterized in that** the gloss has a value > 90% at an angle of 60 and 85° and a value > 85% at an angle of 20° against the standard gloss master (standard A).
7. Recording material according to any of claims 1 to 6, **characterized in that** the substrate is a plastics film.
8. Recording material according to any of claims 1 to 7, **characterized in that** the metal layer contains aluminum, zinc, copper,

nickel, chromium, gold, silver or alloys thereof.

9. Recording material according to any of claims 1 to 8,
characterized in that
the substrate material is a transparent polyester film.
10. Recording material according to any of claims 1 to 9,
characterized in that
the transparent or slightly dull recording layer comprises a hydrophilic film-forming polymer.
11. Recording material according to claim 10,
characterized in that
the hydrophilic film-forming polymer consists of PVA, PVP, cellulose derivatives, (meth)acrylic acid derivatives, vinyl acetate, copolymers thereof or a mixture of these substances.
12. Recording material according to claim 2,
characterized in that
the protective layer is a (meth)acrylate polymer or copolymer.

Patentansprüche

1. Aufzeichnungsmaterial für das Inkjet-Verfahren mit einem Trägermaterial, das mindestens auf einer seiner Oberflächen eine Metallschicht aufweist und auf dieser Metallschicht eine transparente oder geringfügig mattierte Aufzeichnungsschicht für wäßrige Tinten vorhanden ist, wobei der Glanz, gemessen auf der Oberfläche der Aufzeichnungsschicht, nach DIN 67530 gegen einen Glanzstandard A bei Messung unter einem Winkel von 20°, 60° und 85° einen Wert >70% aufweist.
2. Aufzeichnungsmaterial nach Anspruch 1, dadurch gekennzeichnet, daß die Metallschicht mit einer Schutzschicht abgedeckt ist und die transparente oder leicht mattierte Aufzeichnungsschicht für wäßrige Tinten auf dieser Schutzschicht angeordnet ist.
3. Aufzeichnungsmaterial nach Ansprüchen 1 oder 2, dadurch gekennzeichnet, daß das Trägermaterial transparent ist.
4. Aufzeichnungsmaterial nach Ansprüchen 1 oder 2, gekennzeichnet durch ein transparentes Trägermaterial mit einer Metallschicht auf einer ihrer Oberflächen und daß die transparente oder leicht mattierte Aufzeichnungsschicht für wäßrige Tinten auf der gegenüberliegenden Seite des transparenten Trägermaterials statt auf der Metallschicht oder auf der die Metallschicht abdeckenden Schutzschicht angeordnet ist.

5

10

15

20

25

30

35

40

45

50

55

5. Aufzeichnungsmaterial nach Anspruch 1, dadurch gekennzeichnet, daß der Glanz unter einem Winkel von 20°, 60° und 85°, gemessen gegen Glanzstandard A, einen Wert >80% aufweist
6. Aufzeichnungsmaterial nach Anspruch 1, dadurch gekennzeichnet, daß der Glanz unter einem Winkel von 60° und 85° einen Wert von >90% und unter einem Winkel von 20° einen Wert von größer 85%, gemessen gegen Glanzstandard A, aufweist.
7. Aufzeichnungsmaterial nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß der Träger eine Kunststoffolie ist.
8. Aufzeichnungsmaterial nach einem der Ansprüche 1 bis 7, dadurch gekennzeichnet, daß die Metallschicht Aluminium, Zink, Kupfer, Nickel, Chrom, Gold, Silber oder deren Legierung enthält.
9. Aufzeichnungsmaterial nach einem der Ansprüche 1 bis 8, dadurch gekennzeichnet, daß das Trägermaterial eine transparente Polyesterfolie ist.
10. Aufzeichnungsmaterial nach einem der Ansprüche 1 bis 9, dadurch gekennzeichnet, daß die transparente oder geringfügig mattierte Aufzeichnungsschicht ein hydrophiles filmbildendes Polymer enthält.
11. Aufzeichnungsmaterial nach Anspruch 10, dadurch gekennzeichnet, daß das hydrophile filmbildende Polymer aus PVA, PVP, Cellulosederivaten, (Meth)acrylsäurederivaten, Vinylacetat, deren Copolymeren oder einem Gemisch dieser Substanzen besteht.
12. Aufzeichnungsmaterial nach Anspruch 2, dadurch gekennzeichnet, daß die Schutzschicht ein (Meth)acrylpolymer oder Copolymer ist.

Revendications

1. Matériau d'enregistrement par jet d'encre comportant un matériau substrat qui présente, sur l'une de ses surfaces, une couche métallique et, sur cette couche métallique, une couche d'enregistrement transparente ou légèrement mate pour recevoir des encres aqueuses, la brillance mesurée sur la surface de cette couche d'enregistrement, selon la norme DIN 67530 et sous un angle de 20°, 60° et 85°, ayant une valeur > 70% en comparaison avec un témoin de brillance standard (standard A).
2. Matériau d'enregistrement selon la revendication 1, caractérisé par le fait que la couche métallique est recouverte d'un revêtement protecteur et que la couche d'enregistrement transparente ou légèrement mate pré-

- vue pour recevoir des encres aqueuses est placée sur ladite couche protectrice.
3. Matériau d'enregistrement selon l'une des revendications 1 ou 2, caractérisé par le fait que le matériau substrat est transparent. 5
 4. Matériau d'enregistrement selon l'une des revendications 1 ou 2, caractérisé par un matériau substrat transparent présentant une couche métallique sur l'une de ses surfaces et par le fait que la couche d'enregistrement transparente ou légèrement mate prévue pour recevoir des encres aqueuses est placée sur la surface opposée du matériau substrat transparent au lieu de l'être sur la couche métallique ou sur le revêtement protecteur recouvrant la couche métallique. 10 15 20
 5. Matériau d'enregistrement selon la revendication 1, caractérisé par le fait que la brillance, mesurée sous un angle de 20°, 60° et 85, a une valeur > 80% en comparaison avec un témoin de brillance standard (standard A). 25
 6. Matériau d'enregistrement selon la revendication 1, caractérisé par le fait que, mesurée sous un angle de 60° à 85°, la brillance a une valeur > 90% et, mesurée sous un angle de 20°, une valeur > 85%, en comparaison avec un témoin de brillance standard (standard A). 30
 7. Matériau d'enregistrement selon l'une des revendications 1 à 6, caractérisé par le fait que le substrat est un film plastique. 35
 8. Matériau d'enregistrement selon l'une des revendications 1 à 7, caractérisé par le fait que la couche métallique contient de l'aluminium, du zinc, du cuivre, du nickel, du chrome, de l'or, de l'argent ou leurs alliages. 40 45
 9. Matériau d'enregistrement selon l'une des revendications 1 à 8, caractérisé par le fait que le substrat est un film de polyester transparent. 50
 10. Matériau d'enregistrement selon l'une des revendications 1 à 9, caractérisé par le fait que la couche d'enregistrement transparente ou légèrement mate comporte un polymère hydrophile formant un film. 55
 11. Matériau d'enregistrement selon la revendication 10, caractérisé par le fait que le polymère hydrophile formant un film est constitué d'alcool polyvinylique, de polyvinylpyrrolidone, de dérivés de cellulose, de dérivés de l'acide (méth)acrylique, d'acétate de vinyle, de leurs copolymères ou d'un mélange de ces substances.
 12. Matériau d'enregistrement selon la revendication 2, caractérisé par le fait que la couche protectrice est un polymère ou un copolymère de (méth)acrylate.